High-Resolution Oxygen-17 NMR of Solids

Suzanne Schrämm and Eric Oldfield*[†]

Contribution from the School of Chemical Sciences, University of Illinois at Urbana, Urbana, Illinois 61801. Received August 22, 1983

Abstract: We report the observation of well-resolved solid-state oxygen-17 NMR spectra of a variety of oxides and oxyanions by means of high-field (11.7 T) "magic-angle" and "variable-angle" sample-spinning NMR spectroscopy. The results (obtained by observation of the (1/2, -1/2) spin transition) indicate that a very wide range of 17O quadrupole coupling constants (~0 to >5 MHz), chemical shift anisotropies (~ 0 to >300 ppm), and line widths (~ 0.3 to >40 ppm), in addition to the expected overall \sim 1200 ppm isotropic chemical shift range, are to be anticipated in solid-state oxygen-17 NMR studies, giving a rich variety of spectral information. For example, in the SiO_4^{4-} unit of the nesosilicate forsterite (Mg₂SiO₄), each nonequivalent oxygen is partially resolved and split by a large second-order quadrupole interaction, permitting determination of the isotropic chemical shifts, quadrupole coupling constants, and electric field gradient tensor asymmetry parameters for each of the three types of oxygen present. By contrast, in the WO_4^{2-} unit of K_2WO_4 , each of the three crystallographically nonequivalent oxygens is fully resolved, the isotropic chemical shift range being \sim 15 ppm, there is no measurable quadrupole interaction, leading to ~1 ppm line widths, and each oxygen has an ~300 ppm chemical shift anisotropy, $\Delta\sigma$. In order to better predict the types of results to be obtained in future solid-state oxygen-17 NMR studies, we present empirical relationships between quadrupole coupling constant values and an average percent ionic character for several oxides and oxyanions, and between cation ionic radius and chemical shift, for a series of isoelectronic oxides and oxyanions. Overall, the results represent an initial effort in delineating the types of systems amenable to investigation by means of high-field, high-resolution solid-state oxygen-17 NMR spectroscopy and indicate that a very rich variety of oxygen-17 NMR line-width and shift parameters are to be expected for both main-group and transition-metal oxides and oxyanions in the crystalline solid state. Such studies should provide important new parameters for structural characterization of these and other, noncrystalline systems, such as some mineral phases, glasses, ceramics, and heterogeneous catalysts.

There has recently been considerable interest in obtaining high-resolution NMR spectra of quadrupolar nuclei in solids by means of observation of the (1/2, -1/2) spin transitions of nonin-tegral spin quadrupolar nuclei (I = 3/2, 5/2, 7/2, or 9/2) under conditions of "magic-angle" sample spinning (MASS, ref 1-8) and "variable-angle" sample spinning (VASS, ref 4, 9-11). Since it is the most abundant element and is a constituent of most minerals and many other inorganic compounds, the possibilities of carrying out oxygen NMR in the solid state have particular attractions. For example, in most silicates where only one ^{29}Si resonance is observed, 12,13 there may be as many as three or perhaps four nonequivalent oxygen nuclei present.4,14 Observation of each nonequivalent oxygen has the potential of providing even more information than observation of the corresponding cations and is one of the goals of our research. In this paper, we report the results of recent oxygen-17 NMR studies on a variety of oxides and oxyanions. In particular, we discuss with examples some of the factors affecting the resolution of ¹⁷O NMR spectra of solids, in order to try to lay a framework within which to interpret existing results and predict future promising directions for solid-state ¹⁷O NMR spectroscopy in chemistry and geology.

Experimental Methods

Forsterite (Mg₂SiO₄) was prepared from Si¹⁷O₂ and Mg¹⁷O basically as described previously for diopside (CaMgSi₂O₆, ref 4). KMnO₄ and K_2WO_4 were ¹⁷O-labeled by heating the solid materials with $H_2^{17}O$ (containing 40 atom % ¹⁷O; Merck, Sharpe and Dohme, Montreal, Canada) in a sealed tube at 80 °C for 7 days followed by removal of H₂O and crystallization. Labeled $Cs_6V_{10}O_{28}$ was obtained by $H_2{}^{17}O$ exchange of the soluble ammonium form followed by precipitation with CsCl and recrystallization. All three compounds had satisfactory microchemical analysis and ¹⁷O solution chemical shifts. (μ_4 -[¹⁷O]oxo)hexakis(μ -O,Odiisopropylphosphorodithioato)tetrazinc was the generous gift of R. G. Bridger of the Mobil Research and Development Corporation, Princeton, NJ. The synthesis of the other materials are described elsewhere.

All spectra were obtained on a "home-built" 11.7-T NMR spectrometer, which consists of an 11.7-T 52-mm bore superconducting solenoid (Oxford Instruments Company, Osney Mead, Oxford, U.K.), a Nicolet Instrument Corporation (Madison, WI) Model-1180E data acquisition system, and a variety of radiofrequency circuitries. We used an Amplifier Research (Souderton, PA) Model 200L amplifier for pulse amplification.

[†]USPHS Research Career Development Awardee, 1979-1984 (Grant CA-00595).

Samples were in general spun at the "magic angle" in a "home-built" solids NMR probe equipped with an Andrew-Beams type rotor system, at between \sim 3 and 4.5 kHz. Static spectra were obtained in a horizontal solenoid-type sample probe.

Results and Discussion

A number of factors affect the appearance of a solid-state ¹⁷O NMR spectrum. Among them are the following: (a) The magnitude of the quadrupole coupling constant, $e^2 q Q/h$. (b) The magnitude of the isotropic chemical shift, σ_{i} . (c) The magnitude $(\Delta \sigma)$ and asymmetry parameter (η) of the chemical shift tensor. (d) The asymmetry parameter (η^{Q}) of the field gradient tensor. (e) A variety of experimental parameters, including the degree to which transitions other than the (1/2, -1/2) one are excited by the pulse, together with the more mundane considerations of pulse repetition rate with respect to T_1 , etc. In this paper we present results on a-d, and discuss what we believe are some useful correlations with electronic structure for a and b that may have some predictive value for future studies of this type.

Quadrupole Effects in Solid-State ¹⁷O NMR. We show in Figure

Congr. Ampere, 18th 1974, 241. (2) Muller, D.; Gessner, W.; Behrens, H.-J.; Scheler, G. Chem. Phys. Lett. 1981, 79, 59.

(3) Meadows, M. D.; Smith, K. A.; Kinsey, R. A.; Rothgeb, T. M.; Skarjune, R. P.; Oldfield, E. Proc. Natl. Acad. Sci. U.S.A. 1982, 79, 1351. Oldfield, E.; Kinsey, R. A.; Montez, B.; Ray, T.; Smith, K. A. J. Chem. Soc.,

- (4) Schramm, S.; Kirkpatrick, R. J.; Oldfield, E. J. Am. Chem. Soc. 1983, 105, 2483.
- (5) Kundla, E.; Samoson, A.; Lippmaa, E. Chem. Phys. Lett. 1981, 83, 229.
- (6) Burton, D. J.; Harris, R. K. J. Chem. Soc., Chem. Commun. 1982, 256.
 (7) Fyfe, C. A.; Gobbi, G. C.; Hartmen, J. S.; Lenkinski, R. E.; O'Brien, J. H.; Beange, E. R.; Smith, M. A. R. J. Magn. Reson. 1982, 47, 168.
 (8) Frye, J. S.; Maciel, G. E. J. Magn. Reson. 1982, 48, 125.
- (9) Oldfield, E.; Schramm, S.; Meadows, M. D.; Smith, K. A.; Kinsey, R.
- A.; Ackerman, J. J. Am. Chem. Soc. 1982, 104, 919.
 (10) Schramm, S.; Oldfield, E. J. Chem. Soc., Chem. Commun. 1982, 980. (11) Ganapathy, S.; Schramm, S.; Oldfield, E. J. Chem. Phys. 1982, 77, 4360
- (12) Lippmaa, E.; Magi, M.; Samoson, A.; Engelhardt, G.; Grimmer, A.-R. J. Am. Chem. Soc. 1980, 102, 4889.
- (13) Smith, K. A.; Kirkpatrick, R. J.; Henderson, D. M.; Oldfield, E., Am. Mineral. 1983, 68, 1206.
- (14) Schramm, S.; Kirkpatrick, R. J.; Oldfield, E., unpublished results.

⁽¹⁾ Andrew, E. R.; Bradbury, A.; Eades, R. G. Nature (London) 1959, 183, 1802. Tzalmona, A.; Andrew, E. R. Magn. Reson. Relat. Phenom. Proc.



Figure 1. Static and spinning oxygen-17 Fourier transform NMR spectra of some inorganic oxides and oxyanions at 11.7 T (corresponding to an ¹⁷O Larmor frequency of 67.8 MHz) together with the spectral simulation of a covalent (ether) oxygen NMR spectrum. (A) Static MgO, 39 scans, recycle time = 10 s. (B) MASS MgO at 4.5 kHz, 12 scans, recycle time = 30 s. (C) Static Al₂O₃, 1350 scans, recycle time = 30 s. (D) MASS Al₂O₃ at 3.4 kHz, 195 scans, recycle time = 30 s. (E) Static SiO₂, 10 scans, recycle time = 120 s. (F) VASS SiO₂ (θ = 75°) at 4.1 kHz, 47 scans, recycle time = 60 s. (G) Spectral simulation of an ether oxygen having e^2qQ/h = 9.9 MHz, η = 0.6, static spectrum. Values of between 10 and 100 Hz exponential line broadening were used to improve spectral signal-to-noise ratios. The scale is referenced to an external sample of tap water. Adapted from ref 4. The ppm values shown are those observed experimentally.

1 static and spinning ¹⁷O NMR spectra of Mg¹⁷O (Figure 1A,B), α -Al₂¹⁷O₃ (Figure 1C,D), and Si¹⁷O₂ (low cristobalite, a framework or three-dimensional silicate, Figure 1E,F),⁴ in addition to a simulated spectrum of a typical covalent oxygen, that in xanthene (Figure 1G, ref 15). The results indicate a wide range of electric quadrupole coupling constants, varying from ~ 0 MHz in MgO to ~2.2 MHz for the oxygens in α -Al₂O₃,¹⁶ ~5.8 MHz for the oxygens in SiO₂,^{4,17} and ~10 MHz for the oxygen in xanthene.¹⁵ Because of the potentially very large magnitude of the quadrupole interaction, the size of the electric field gradient at the ¹⁷O nucleus determines, to a first approximation, the type of NMR spectrum to be obtained in solid-state ¹⁷O NMR studies. For example, the ¹⁷O MASS NMR spectrum of MgO contains a single line of ≤ 0.3 ppm width, in the crystalline solid state, an extraordinarily narrow breadth due to the highly symmetric nature of the O²⁻ anion in the cubic MgO lattice.¹⁸ By contrast, the spectrum of SiO_2 $(e^2 q Q/h \sim 5.8 \text{ MHz})$ contains a well-resolved second-order powder pattern⁴ that is effectively narrowed under VASS conditions (Figure 1E,F, ref 4), while spectra of the purely covalent oxides (ethers) are essentially inaccessible with current operating field strengths, since $e^2 q Q/h$ values are ~10 MHz.¹⁵

The results of Figure 1 indicate that "high-resolution" ¹⁷O NMR spectra of some oxides may be obtained but do not demonstrate the actual resolution of any nonequivalent oxygen sites. We therefore show in Figure 2 11.7-T ¹⁷O MASS NMR spectra of



Figure 2. ¹⁷O MASS NMR spectra (11.7 T), and spectra simulations, of Mg₂Si¹⁷O₄ (forsterite). (A) MASS NMR spectrum, 370 scans at a 120-s recycle time using a 10- μ s pulse excitation. (B) Expansion of A. (C) Spectral simulation of B using parameters of D-F. (D) Component 1, $\sigma_i = 61$ ppm, $e^2qQ/h = 2.35$ MHz, $\eta = 0.20$, 50% intensity. (E) Component 2, $\sigma_i = 62$ ppm, $e^2qQ/h = 2.35$ MHz, $\eta = 1.0$, 18% intensity in the center band. (F) Component 3, $\sigma_i = 47$ ppm, $e^2qQ/h = 2.70$ MHz, $\eta = 0.3$ 18% intensity in the center band. Residual spectral intensities are located in the sidebands of components 2 and 3. The scales are referenced to an external sample of tap water; the errors in σ_i are about ± 1 ppm.

the olivine type monosilicate, forsterite (Mg_2SiO_4) , in which considerable structure is apparent, Figure 2A. The results of Figure 2A strongly suggest that at least three types of nonequivalent oxygen are present per SiO₄⁴⁻ unit, and in Figure 2B,C, we show an expansion of the center-band resonances of forsterite (Figure 2B), together with a spectral simulation of the line shape observed (Figure 2C). The results of the simulation indicate that there are three types of oxygen present, characterized by isotropic chemical shifts, quadrupole coupling constant, and electric field gradient tensor asymmetry parameters of 61 ppm, 2.35 MHz, and 0.2 (2 oxygens, Figure 2D), 62 ppm, 2.35 MHz, and 1.0 (1 oxygen, Figure 2E), and 47 ppm, 2.70 MHz, and 0.3 (1 oxygen, Figure 2F). Thus, the results of Figure 2 indicate that well-resolved oxygen-17 NMR spectra of simple oxyanions, containing nonequivalent oxygen atoms, may be readily observed by means of high-field MASS NMR techniques.

In principle, ab initio calculations should readily provide the desired quadrupole coupling constant (or electric field gradient tensor) information required for at least a preliminary prediction of the nature of the solid-state ¹⁷O NMR spectra of any given oxide or oxyanion. In the absence of such results, however, we have found that an empirical relation based on the ionic character of the cation-oxygen bonds, obtained by means of the Pauling electronegativities, gives a useful estimate of the magnitude of $e^2 q Q/h$ to be expected in a given bonding situation. Results are shown in Figure 3 for MgO, K₂WO₄, ZnO, Mg₂SiO₄, CaMgSi₂O₆, α -Al₂O₃, B₂O₃, low cristobalite, H₂O, 2,5-dichlorohydroquinone, p-chlorophenol, tetrachlorohydroquinone, xanthene, tetrahydropyran, and N-methyl syndone.¹⁹ Percent ionic characters for the nonsymmetric interactions are average values based on the two strongest interactions, e.g., W-O and O-K in K2WO4, C-O and O-H in tetrachlorohydroquinone, and so on.

Although very approximate, we believe the results of Figure 2, which may be represented as

$$e^2 q Q / h (\text{MHz}) = -0.203 I(\%) + 14.78$$
 (1)

where I is the ionic character in percent and the correlation coefficient is ~ 0.96 , are a useful initial guide as to what oxides

⁽¹⁵⁾ Hsieh, Y.; Koo, J. C.; Hahn, E. L. Chem. Phys. Lett. 1972, 13, 563.
(16) Brun, E.; Derighetti, B.; Hundt, E. E.; Niebuhr, H. H. Phys. Lett. A 1970, 31A, 416.

⁽¹⁷⁾ Bray, P. J.; Bucholtz, F.; Geissberger, A. E.; Harris, I. A. Nucl. Instrum. Methods 1982, 199, 1.

⁽¹⁸⁾ Skinner, B. J. Am. Mineral. 1957, 42, 39.

⁽¹⁹⁾ Kinzinger, J.-P In "NMR Basic Principles and Progress"; Diehl, P., Fluck, E., Kosfeld, R., Eds.; Springer-Verlag: New York, 1982; Vol. 17, p 1.



Figure 3. Plot of ¹⁷O electric quadrupole coupling constant (e^2qQ/h) , MHz) vs. average percent ionic character for a series of A-O-B fragments, where A and B are cations. The experimental $e^2 q Q/h$ values are for a series of oxides or simple oxyanions. The percent ionic character is the arithmetic mean of the single-bond values obtained from the Pauling electronegativities of elements A, B, and O. Species more covalent than SiO₂ are best studied by NQR or wide-line NMR methods, while more ionic systems are amenable to "high-resolution" solid-state MASS and VASS NMR techniques. The straight line is the leastsquares fit of the data to eq 1. Compounds used were as follows: (a) N-methylsyndone, (b) tetrahydropyran, (c) xanthene, (d) tetrachlorohydroquinone, (e) 2,5-dichlorohydroquinone, N-methylsyndone, pchlorophenol, (g) normal hexagonal ice, (h) B₂O₃, (i) low cristobalite, (j) diopside, (k) forsterite, (l) Al₂O₃, (m) zinc oxide, (n) potassium tungstate, (o) magnesium oxide.

or oxyanions are likely candidates for high-resolution solid-state NMR studies.

For example, at 11.7 T (corresponding to an ¹⁷O resonance frequency of 67.8 MHz), the results of Figures 1-3 indicate that elements with electronegativities in excess of ~ 1.8 , bound to oxygen, may preclude the ready determination of high-resolution ¹⁷O NMR spectra at currently available magnetic field strengths. Thus SiO₂ (Si EN = 1.8) has an $e^2 q Q/h$ value of ~5.8 MHz.^{4,17} At 67.8 MHz, this corresponds to a second-order powder pattern line breadth of the (1/2, -1/2) transition of ~20 kHz.^{3,11} By use of MASS, a complex line shape is obtained, however, by VASS, the first-order sideband is absent^{4,10,11} and a well-resolved center band is obtained (Figure 1). Clearly then, we would not expect it to be a straightforward matter to obtain high-resolution solid-state ¹⁷O NMR spectra of more covalent species, e.g., B₂O₃ (B EN = 2.0), SO₃ phases (S EN = 2.5), or I_2O_5 (I EN = 2.5), while, as shown in Figures 1-3, spectra of more electropositiveelement-containing species such as MgO and Al₂O₃ are readily obtained (Mg EN = 1.2, Al EN = 1.5).

While such predictions are clearly very crude, we believe they have some utility since they are simple to make and so far seem to be correct in indicating which oxides and oxyanions are suitable candidates for high-resolution MASS and VASS NMR in the solid state. Naturally, the presence of multiple (π) bonding will have additional complicating effects on the appearance of such ¹⁷O NMR spectra, as shown below, and of course the simple relation can be forced to break down by invoking any array of ligands that gives perfect cubic symmetry.

Chemical Shift Effects in Solid-State ¹⁷O NMR. The results of Figure 3 indicate that a wide variety of transition-metal oxides and oxyanions should be accessible to study by means of solid-state ¹⁷O MASS and VASS NMR spectroscopy, since the electronegativities of these metals are all moderate, and at least in the oxyanions there will often be highly electropositive counterions present. In the absence of large quadrupole interactions, we may thus expect to see chemical shift resolved resonances, in addition to perhaps being able to obtain information on chemical shielding tensor interactions.

We show therefore in Figure 4 results on two typical transition-metal oxyanions, KMnO₄ and K₂WO₄. In Figure 4A we



Figure 4. 67.8-MHz oxygen-17 Fourier transform NMR spectra (obtained at a magnetic field strength of 11.7 T) at 23 °C of (A) KMnO₄ as a static solid, while spinning at the "magic-angle", and as an aqueous solution, (B) K₂WO₄, while spinning at the "magic-angle" and (inset) as an aqueous solution. All samples were ¹⁷O enriched as discussed in the text. Typically, from 50 to 200 scans, at a 5-30-s recycle time, were acquired with $\sim 90^{\circ}$ pulse excitation. The MASS spinning rates were 3.6 (KMnO₄) and 3.2 kHz (K₂WO₄). In K₂WO₄, all three crystallographically nonequivalent oxygen atoms are resolved. The numerous sets of resonances in B are due to a large ¹⁷O chemical shift anisotropy and are generated via the sample-spinning process.

present the 67.8-MHz ¹⁷O NMR spectrum of KMn¹⁷O₄, both as a static crystalline solid, under 3.6-kHz "magic-angle" rotation, and as an aqueous solution. The line width of the static solid $(\sim 2.4 \text{ kHz}, \sim 35 \text{ ppm})$ is due to a combination of K, Mn, and O dipole-dipole, second-order quadrupole, chemical shift anisotropy, chemical shift nonequivalence, and Mn-O indirect spin-coupling interactions. A rather featureless line is obtained (as with the ⁵⁵Mn resonance in KMnO₄, ref 6, 11). Upon MASS, a narrow (~400 Hz, ~6 ppm) symmetric resonance at 1197 ppm downfield from external $H_2^{17}O$ is obtained (in contrast to the characteristic line shape observed for ⁵⁵Mn in KMnO₄, due to a second-order quadrupole interaction), indicating that $e^2 q Q/h$ is $\lesssim 0.4$ MHz. The residual line breadth is considerably greater than that for $KMn^{17}O_4$ in aqueous solution (Figure 4A), but we cannot accurately deduce the relative contributions of the residual interactions. Note that each ¹⁷O nucleus appears essentially magnetically equivalent in the rotating solid, consistent with the X-ray structural determination.²⁰

In sharp contrast to the results of Figure 4A we show in Figure 4B solution and crystal MASS NMR spectra of $K_2W^{17}O_4$. Clearly, the MASS NMR spectra of Figure 4A,B contain a number of remarkable differences. First, the spectrum of Figure 4B contains 10 groups of three lines. The frequency separations between the 10 groups correspond to the spinning frequency (3.2 \pm 0.1 kHz) and change with spinning rate, while the separations between the three peaks remain constant. Thus, peaks 1, 2, and 3 represent the isotropic chemical shifts of the three nonequivalent oxygens in the WO_4^{2-} ion.²¹ The sum of the intensity of peak 1 and its sidebands is twice that of either peak 2 or 3 and their respective sidebands, thus peak 1 almost certainly corresponds to the two crystallographically equivalent oxygens in the WO_4^{2-} ion.21

⁽²⁰⁾ Palenik, G. J. Inorg. Chem. 1967, 6, 503. (21) Koster, A. S.; Kools, F. X. N. M.; Rieck, G. D. Acta Crystallogr., Sect B 1969, B25, 1704.



Figure 5. Plot of ${}^{17}O$ (solution) chemical shift (ppm from $H_2{}^{17}O$) vs. (crystal) cation ionic radius (Å) for a series of oxides and oxyanions isoelectronic with MnO_4^- . The straight line is the least-squares fit of the data to eq 2 in the text. Ionic radii from: Kordes, E. Z. Phys. Chem., Abt. B 1939, 43, 213. Ahrens, L. H. Geochim. Cosmochim. Acta 1952, 2, 155.

From Figure 4B we find that the isotropic chemical shifts of the ¹⁷O nuclei in K₂WO₄ are 437, 429, and 422 \pm 1 ppm from external $H_2^{17}O$. In addition, analysis of the sideband intensity ratios of peaks 1, 2, and 3 as a function of spinning speed according to the method of Herzfeld and Berger²² yields the following *chemical shift tensors* for peaks 1, 2, and 3: $\sigma_{11}^{-1} = 564$, $\sigma_{22}^{-1} = 530$, and $\sigma_{33}^{-1} = 217$ ppm; $\sigma_{11}^{-2} = 567$, $\sigma_{22}^{-2} = 518$, and $\sigma_{33}^{-2} = 202$ ppm; $\sigma_{11}^{-3} = 561$, $\sigma_{22}^{-3} = 497$, and $\sigma_{33}^{-3} = 208$ ppm, where the values for σ^1 represent the shift tensor for the two equivalent oxygens in the WO_4^{2-} ion. This is the first observation of solid-state ¹⁷O chemical shielding tensors we are aware of. The mean ¹⁷O solid-state chemical shift of peaks 1 (2 oxygens), 2, and 3 is 431 \pm 1 ppm, in good agreement with the solution value (422 ppm, Figure 4B; 420 ppm, ref 23).

The widths of the individual peaks in Figure 4B are somewhat narrower than with KMnO₄, due in part we believe to the absence of an abundant spin species (⁵⁵Mn is 100% abundant, $I = \frac{5}{2}$; ¹⁸³W is 14% abundant, I = 1/2).

The results of Figure 4A,B indicate that very narrow line widths may be obtained for some oxyanions, because of small (a few hundred kilohertz) $e^2 qQ/h$ values, due presumably to relatively weak M-O bonds.

In order to once again make a perhaps more chemically useful interpretation of at least some of the large differences in the NMR parameters (chemical shifts) observed for the two isoelectronic species (MnO₄⁻, 1197 ppm; WO₄²⁻, 431 ppm), we now discuss briefly the topic of ¹⁷O NMR chemical shifts.

As is well-known, for most of the heavier elements the paramagnetic term, σ_p , dominates the shielding of a given nucleus. As originally pointed out by Freeman et al.²⁴ a linear relation between NMR frequency and the wavelength of the lowest frequency optical absorption (at least for octahedral Co(III) complexes) exists, as it does for a series of oxyanions.²³ Carrington et al.^{25,26} observed a similar linear relationship between the first absorption maxima of a series of isoelectronic transition-metal oxides and oxyanions (MnO₄⁻, RuO₄, CrO₄²⁻, OsO₄, TcO₄⁻, VO₄³⁻, ReO_4^- , MoO_4^{2-} , WO_4^{2-}) and cation ionic radius. In addition, we and others^{13,27} have recently observed a linear relationship between Si-29 chemical shift and Si-O bond length (or cation-oxygen bond energy) in a variety of silicates, and there naturally exists a relationship between ionic radius and bond length for a series of

(22) Herzfeld, J.; Berger, A. E. J. Chem. Phys. 1980, 73, 6021.

- (23) Figgis, B. N.; Kidd, R. G.; Nyholm, R. S. Proc. R. Soc. London, Ser. A 1962, 269, 469.
- (24) Freeman, R.; Murray, G. R.; Richards, R. E. Proc. R. Soc. London, Ser. A. 1957, 242, 455
- (25) Carrington, A.; Schonland, D.; Symons, M. C. R. J. Chem. Soc. 1957, 659
- (26) Carrington, A.; Symons, M. C. R. J. Chem. Soc. 1960, 889.
 (27) Higgins, J. B.; Woessner, D. E. EOS, Trans. Am. Geophys. Union Abstr. 1982, 63, 1139. (28) Grimmer, A.-R.; Peter, R.; Fechner, E.; Molgedey, G. Chem. Phys.
- Lett. 1981, 77, 331. (29) Tossell, J. A., private communication.



Figure 6. 67.8-MHz oxygen-17 Fourier transform NMR spectra of $(\mu_4$ -oxo)hexakis $(\mu$ -O,O-diisopropylphosphorodithioato)tetrazinc (basic zinc dithiophosphate, $Zn_4O(dtp)_6$) and ammonium and cesium decavandates $(V_{10}O_{28}^{6-})$. (A) Zn₄O(dtp)₆ in CHCl₃ solution, 697 scans at a 5-s recycle time. (B) Solid $Zn_4O(dtp)_6$, MASS NMR at 3.7 kHz, 2260 scans at a 5-s recycle time. (C) $(NH_4)_6V_{10}O_{28}$ in H₂O solution, 258 scans at a 30-s recycle time. (D) $Cs_6V_{10}O_{28}$ MASS NMR at 4.2 kHz, 526 scans at a 120-s recycle time.

structurally similar compounds. These various empirically established relationships are illustrated below:



It thus seems plausible to expect a correlation between cation ionic radius and oxygen-17 chemical shift in a series of isoelectronic structures, and the results of Figure 5 for a series of group 5B, 6B, 7B, and 8 oxides and oxyanions show that this is indeed the case. The results are fitted by

$$\delta$$
 (ppm) = -4394r (Å) + 3205 (2)

with a correlation coefficient of 0.92. We believe this and other similar curves may be of use in predicting ¹⁷O chemical shifts, both in solution and in the crystalline solid state. Indeed, the correlation shown above indicates a possible error in the reported chemical shift of MoO_4^{2-} reported in ref 19 and that the correct value is 530 ppm (ref 23 and our unpublished results), both in solution and in the crystalline solid state.

Results on More Complex Species. The results of Figures 1-5 were obtained on rather simple oxides and oxyanions. We show therefore in Figure 6¹⁷O solid-state MASS NMR spectra of two more complex species: a basic zinc dithiophosphate ($(\mu_{a}-1^{17}O)$ oxo)hexakis(μ -O,O-diisopropylphosphorodithioato)tetrazinc) and cesium decavanadate ($Cs_6V_{10}^{17}O_{28}$), a polyoxy anion related to the naturally occurring mineral, pascoite $(Ca_3V_{10}O_{28}\cdot 17H_2O)$.

The basic zinc dithiophosphate, $Zn_4O(dtp)_6$, is thought to have a structure similar to that of the basic beryllium and zinc acetates,³⁰ containing a tetrahedral μ_4 -oxo group. On the basis of symmetry grounds alone, we might thus expect $e^2 q Q/h \sim 0$, and the results of Figure 6 are consistent with this expectation. The ¹⁷O MASS NMR spectrum (Figure 6B) contains a narrow center band (width ≤ 200 Hz) at -48.8 ppm, while the solution spectrum

⁽³⁰⁾ Bridger, R. F., 24th Experimental NMR Conference, Asilomar, CA, April 10-14, 1982, Abstract B-3.

(Figure 6A and ref 30) contains a very narrow resonance at -48 ppm.³⁰ The additional sideband features present in Figure 6B arise, we believe, from the satellite $(\pm^{1}/_{2} \leftrightarrow \pm^{3}/_{2}; \pm^{3}/_{2} \leftrightarrow \pm^{5}/_{2})$ transitions. Similar results are predicted for the basic beryllium and zinc acetates and for the μ_{6} -oxo atoms in the $V_{10}O_{28}^{6-}$ ion. Such predictions are borne out for O_A (see, e.g., ref 31 for no-menclature) in the $V_{10}O_{28}^{6-}$ ion, as shown in Figure 6.

In Figure 6C we show the spectrum of the $V_{10}O_{28}^{6-}$ ion in H_2O solution, and the integrated peak intensities are as expected.³¹ \tilde{O}_A (2), O_B (4), O_C (8), O_D (2), O_E (4), O_F (4), and O_G (4). All lines are quite narrow, except for OF,G which show partially resolved splittings, presumably due to ${}^{1}J_{^{51}V^{-17}O}$ interactions. In the crystalline solid state (as the Cs salt rather than the $\mathrm{NH_4^+}$ salt to reduce dipolar interactions) the overall spectrum is, however, quite different, Figure 6D. The μ_6 -oxo atom (O_A) has a very similar chemical shift (52.0 ppm) to that observed in solution (63.3 ppm). This result is consistent with the observation of a very sharp solution line width for $O_A{}^{31}$ (Figure 6C) and simply indicates a very high symmetry O^{2^-} environment, as in the case of the Zn₄O(dtp) species (Figure 6B). However, the only other resonance in the solid-state ¹⁷O NMR spectrum of $Cs_6V_{10}O_{28}$ to clearly correspond to the solution-state chemical shift and line width is that of O_B , the μ_3 -O site. The more complex features of the $Cs_6V_{10}O_{28}$ spectrum will be discussed in more detail elsewhere.³²

Concluding Remarks. The results presented in this paper represent our first attempts at obtaining and interpreting the ¹⁷O solid-state NMR spectra of a variety of oxides an oxyanions, which we have carried out in order to provide a basis for further studies of related systems of catalytic and geochemical interest. Our results indicate that a very wide range of quadrupole coupling, chemical shift, and chemical shift anisotropy values are to be expected for ¹⁷O nuclei in solids. We have presented results which indicate that species more covalent than silica (Si–O–Si) are unlikely to be amenable to investigation with either ¹⁷O MASS or VASS NMR techniques with currently available magnetic field strengths. For the silicates themselves, however, even modest increases in magnetic field strengths (e.g., $500 \rightarrow 600$ MHz ¹H

(31) Klemperer, W. G.; Shum, W. J. Am. Chem. Soc. 1977, 99, 3544. (32) Schramm, S.; Oldfield, E., unpublished results. resonance frequency) will provide very significant (\sim 50%) increases in spectral resolution, since for such systems resolution improves *quadratically* with increasing magnetic field strength.^{3,4,11}

Our results with the simple SiO_4^{4-} and WO_4^{2-} species illustrate the potential power of solid-state ¹⁷O NMR spectroscopy. Even in very simple oxyanions we have shown that nonequivalent oxygen atoms may be resolved, and that quadrupole coupling constants, chemical shift tensors, and their asymmetry parameters may be determined. Our results indicate that very large chemical shift anisotropies (some 300 ppm) are observed with some oxyanions (which also have vanishingly small $e^2 q Q/h$ values), and our unpublished results on metal carbonyls³³ indicate that $\Delta \sigma$ values as large as 600 ppm are to be expected for some species. We thus believe that the results presented in this publication indicate a very promising future for ¹⁷O solid-state NMR studies in chemistry and geochemistry, especially for the structural analysis of systems not readily investigated by single-crystal X-ray diffraction techniques, by means of future detailed analyses of solid-state chemical shift and quadrupole coupling constant information.

Acknowledgment. We thank R. F. Bridger of the Mobil Research and Development Corporation, Princeton, NJ, for the sample of ¹⁷O-labeled $Zn_4O(dtp)_6$, R. J. Kirkpatrick, for the sample of ¹⁷O-labeled forsterite, and D. M. Henderson and R. J. Kirkpatrick for useful discussions. This work was supported in part by NIH, NSF, the American and Illinois Heart Associations, and the Mobil Foundation, by an Arnold O. Beckman Research Award from the University of Illinois, and has also benefitted from facilities made available through the University of Illinois–National Science Foundation Regional NMR Instrumentation Facility.

Registry No. ¹⁷O, 13968-48-4; B_2O_3 , 1303-86-2; $CaMgSi_2O_6$, 14483-19-3; Mg_2SiO_4 , 15118-03-3; Al_2O_3 , 1344-28-1; ZnO, 1314-13-2; K_2WO_4 , 7790-60-5; MgO, 1309-48-4; *N*-methylsyndone, 6939-12-4; tetrahydropyran, 142-68-7; xanthene, 92-83-1; tetrachlorohydroquinone, 87-87-6; 2,5-dichlorohydroquinone, 824-69-1; *p*-chlorophenol, 106-48-9; cristobalite, 14464-46-1; ice, 7732-18-5.

(33) Keniry, M. A.; Shinoda, S.; Brown, T. L.; Oldfield, E, unpublished results.

Two-Dimensional Heteronuclear Chemical Shift Correlation Spectroscopy in Rotating Solids

James E. Roberts, Shimon Vega,[†] and Robert G. Griffin*

Contribution from the Francis Bitter National Magnet Laboratory, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139. Received September 22, 1983

Abstract: Two-dimensional NMR methods for performing heteronuclear chemical shift correlation experiments in rotating solids are described. The general approach involves both homo- and heteronuclear decoupling during the evolution (t_1) period followed by a coherence transfer or mixing period (τ_{mix}) in which information is transferred between the spin reservoirs. During the detection (t_2) period heteronuclear decoupling is employed and the NMR signals are observed in the customary fashion. Several methods for coherence transfer are discussed, and it is concluded that the method of choice will likely be sample dependent. Three different classes of two-dimensional spectra will be observed in these experiments—containing sidebands in neither, one, or both spectral dimensions—and examples of each type are described. Finally, the occurrence of rotor frequency lines in multiple-pulse/magic-angle sample spinning ¹H spectra is discussed.

Introduction

Despite the availability of sophisticated pulse sequences that attenuate the proton-proton dipolar interaction,¹ the task of obtaining high-resolution proton spectra of polycrystalline powders remains difficult. The residual line widths obtained with multiple-pulse sequences during magic-angle sample spinning (MASS) are typically 2 ppm.^{2–4} When compared to the normal 10–15-ppm

⁺On leave from the Isotope Department, Weizmann Institute of Science, Rehovoth, Israel.

^{(1) (}a) Mehring, M. "High Resolution NMR in Solids", 2nd ed.; Springer-Verlag: Berlin, 1983. (b) Haeberlen, U. "High Resolution NMR in Solids, Selective Averaging"; Academic Press: New York, 1976.